



# Liquid Viscosities

Chart of Approximate Viscosities of Common Liquids	Viscosity in Centipoise @ 70°F	SSU Approximate
Sulfuric Acid	0.2	
Methyl Ethyl Ketone	0.4	
Water	1	
Milk	3	
Oil – Crude	15	80
Ethylene Glycol	16	80
Oil – Auto SAE 10	65	310
Oil – Corn	72	350
Oil – Auto SAE 20	125	585
Oil – Auto SAE 30	200	980
Varnish – Spar	420	2,050
Oil – Auto SAE 60	1,000	4,600
Honey	3,000	14,500
Ink	45,000	
Vaseline Petroleum Jelly	64,000	
Corn Syrup	110,000	

## Component Materials

GPI offers Component Materials to assist with chemical compatibility. In some cases, trade names may be more common than the generic name. The cross reference chart below provides the generic material name and the corresponding trade name.

Generic Material Name	Trade Name
Acetal	Celcon or Delrin
Buna-N, NBR or Nitrile	Chemivic or Krynac
EPDM	Epcar
FKM or fluorocarbon	Fluorel or Viton
Nylon or polyamide	Zytel
PBT polyester	Valox
PEEK	Victrex
Perfluoroelastomer	Kalrez
Perfluoroelastomer	Chemraz
PET polyester	Rynite
Polyester film	Mylar
PPS	Ryton
PTFE	Teflon
PVDF	Kynar